

## Saratoga U.S.A. White Top Quality Neutral Silicone Sealant for Mirrors

Saratoga U.S.A. White Top Quality Neutral Silicone Sealant for Mirrors is a neutral one-component silicone sealant that reticulates thanks to the contact with the air humidity.

### APPLICATION FIELDS

Saratoga U.S.A. White Top Quality Neutral Silicone Sealant for Mirrors is a silicone expressly formulated for elastic bondings on wood, concrete, plastic laminate and metals. Excellent even on treated and reflecting glasses. It is a high elasticity and excellent durability silicone, has excellent resistance to UV rays and bad weather.

### APPLICATION

- All surfaces must be clean, dry, degreased and with no crumbly parts.
- Extrude the sealant in vertical and parallel lines, of about 10 mm width and spaced at 15-25 cm (allows ventilation).
- Apply the mirror pressing uniformly to enlarge the bonding surface.
- Provide a temporary support for the mirror until the sealant has dried (at least 24-72 hours, according to its weight and the quantity of adhesive used).
- Do not apply on the whole surface to bond to not slow down the polymerization process; do not apply the sealant along mirror outer edge (does not allow ventilation).
- Clean within 10 minutes with Saratoga Via•Sil Fresco or a clean cloth wetted with solvent. When cured, clean with Saratoga Via•Sil Indurito.

| Specific data:          | transparent   | white |
|-------------------------|---------------|-------|
| Kind of sealant         | Alcoxy        |       |
| Specific weight         | 1,02          | 1,51  |
| Consistency             | Thixotropic   |       |
| Extrusion rate g/min.   | 15-25         |       |
| Working time (minutes)  | 10            |       |
| Cure time*              | 2-3 mm/24 h   |       |
| Application temperature | +5 / +40 °C   |       |
| Working movement        | 25 %          |       |
| Temperature resistance  | -50 / +150 °C |       |
| Shore A hardness        | 20            |       |
| Elongation at break     | >450 %        |       |
| Elastic recovery        | >90 %         |       |

\*According to humidity, temperature and thickness applied

### STORAGE AND SHELF LIFE

Between +20 and +25°C its shelf life is 12 months since manufacturing date.

### CAUTIONS

Keep out of the reach of children.

Consult Material Safety Data Sheet for full list of hazards and the directions on the product label itself.

For further information, please visit our site [www.saratoga.it](http://www.saratoga.it)

| Product Description | Pack size | Product code | Box quantity | EAN Code        |
|---------------------|-----------|--------------|--------------|-----------------|
| Transparent         | 280 ml    | 85 414 001   | 15           | 8 005860 854147 |
| White               | 280 ml    | 85 414 002   | 15           | 8 005860 990432 |



10/17/2016, 1<sup>st</sup> Rev- The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings . All the information herein do not involve the assumption of responsibility in case of damages. Before using the product, the user should carry out any necessary test in order to ensure that the product is suitable for the intended application. All users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, for specific features, please contact Saratoga Int Sforza spa. Our specialists are at your disposal for further information.